ichemco
Developing Chemical Excellence

member of Afera

CERTIFIED MANAGEMENT SYSTEMS
CERTIQUALITY
UNI EN ISO **9001:2015**
UNI EN ISO **14001:2015**
UNI ISO **45001:2018**

Solacril 753

(Provisional)

Description

SOLACRIL 753 is a solvent self cross-linking acrylic pressure sensitive adhesive.

It has high tack and peel adhesion and medium cohesion.

Application

SOLACRIL 753 is suitable for the production of double-sided tapes.

It is recommended for low temperature applications.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	50±1
3. Brookfield Viscosity 25°C	mPa.s	2000 - 6000 (1)
Solvents		ethylacetate / heptane / isopropyl alcohol

(1) N. 4 RV; 20 RPM

Film properties

Method of analysis	MU	Standard
11. Peel Adhesion on Steel	g/in	1,000
22. Static Shear	h	> 50
97. Loop Tack Test	g	800

Average values; 22±2 g/m² of dry adhesive on PET film 36 µm

Handling

SOLACRIL 753 is supplied ready for coating by rotating blade or reverse roll. Diluted, it can be applied by rotogravure or Mayer bar. A perfect drying is necessary to fully complete the cross-linking process.

Packaging

The product is supplied in iron drums (180 kg).

Storing

Store in a cool place, protected from direct sunlight and heat sources, at temperatures between +5 and +40°C. Keep material in tightly closed containers to prevent loss of solvents.

Use within 6 months from production date (unopened and in the original packaging).

Build date 11 Sep 2025

Above information is reliable, but does not constitute warranty.

ICHEMCO srl
via 11 Settembre, 5 - 20012 CUGGIONO (MI) - ITALY
Phone: +39 02 97243.1 - info@ichemco.it - www.ichemco.it