



Curing Agent W 18

(Provisional)

Description

CURING AGENT W 18 is a bi-functional aziridine crosslinker diluted in dipropylene glycol methylether.

Application

The product is designed to improve cohesion, hydrolysis and chemicals resistance of resins, binders and adhesives.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	19±1
24. Density	g/ml	0.945 - 0.985

when not in use.

Use within 6 months from production date (unopened and in the original packaging).

Handling

CURING AGENT W 18 can be used both in solvent and waterborne systems. The quantity to add must be defined according to the process; as a start, we recommend staying in the range of 1-3%. CURING AGENT W 18 must be added to the product while stirring. Pot life is longer than typical crosslinkers, but needs to be verified on each system. CURING AGENT W 18 is not suitable for the production of 1K systems.

Packaging

The product is supplied in iron drums (25 kg); iron drums (200 kg); IBC containers (1000 kg).

Storing

Store in the original container in a cool and ventilated area. Keep container well sealed,