ichemco
Developing Chemical Excellence

CERTIFIED MANAGEMENT SYSTEMS
CERTIQUALITY
UNI EN ISO 9001:2015
UNI EN ISO 14001:2015
UNI ISO 45001:2018

Release G 100 ES

(Provisional)

Description

RELEASE G 100 ES is a synthetic polymer with an elevated molecular weight in a 100% solid form. When in solution, it is a very efficient release agent for tapes with a superior resistance to heat and humidity.
Its particular chemical structure guarantees an excellent anchorage to polyolefins and a good NO-NOISE effect. RELEASE

Application

RELEASE G 100 ES can be used on corona treated as well as on untreated films.
Concentrations ranges from 0.5% to 3% solids depending upon film type, coating equipment and desired release effect.
RELEASE G 100 ES is soluble in aromatic (e.g. toluene) and aliphatic solvents. (e.g. heptane/isopropylalchol 3:1 or octane/isopropylalcool 3:1) at temperatures above 35°C during the whole process. In order to achieve a continuos and homogeneous coating it is absolutely necessary that the solution is kept at a temperature above 35°C during the whole process.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	> 99.5
5. Melting Range	°C	90 - 98

Handling

Slowly add RELEASE G 100 ES to solvent under continuous stirring. If necessary, heat at 40-50°C. Extra case while Handling flammable solvents is advisable.

Packaging

The product is supplied in fibre drums (20 kg).

Storing

RELEASE K 100 ES in 100% solid form can be stored safely at almost all temperatures below its melting point. In solution, it must be stored at temperatures not below 25°C to prevent gelification. In case of partial or total solidification, store the product in a heated place and stir it well at a temperature between 35°C to 50°C before using. The product will return as fluid as before. Do not coat if the solution is not completely clear or if gelification occured.

Use within 24 months from production date (unopened and in the original packaging).

Build date 11 Sep 2025

Above information is reliable, but does not constitute warranty.

ICHEMCO srl
via 11 Settembre, 5 - 20012 CUGGIONO (MI) - ITALY
Phone: +39 02 97243.1 - info@ichemco.it - www.ichemco.it